



Chukum, USA Ancient Mayan Plaster Based in Merida, MX & Miami, FL.

■ PRODUCT DESCRIPTION:

Chukum Extra Fine Paste is a cement-based coating, ideal for polished finishes. It is complemented with water or Chukum natural resin waters, leaving surfaces completely smooth and with the dimension of your choice. The product can be applied on drywall, Durock and more rustic finishes.

- Apply on a smooth surface.
- Apply at a minimum 3mm to a maximum 5mm thick.

■ BENEFITS:

- -It only requires water to mix or Chukum resin water.
- -Easy application and provides an excellent finish.
- -Resistant to humidity and moisture.
- -It is easily applied with a metal trowel.
- -Due to its properties it allows for repairs.

COLORS:

White | Gray | Cream More colors available upon request.

It is recommended to apply a varnish or sealer at the end of the application, for added protection.



Yield = 86.11 SF (8 m²) Bag: 44 lb (20 kg)



EXTRA-FINE PASTE CHUKUM COEXIST WITH NATURE



STEPS FOR PREPARATION

- Clean well the area where the EXTRA-FINE PASTE will be applied, avoiding paint or loose particles on the surface where it will be applied.
- It is advisable to apply with a roller and adhesion bridge such as Adikum or similar to generate a protective layer between the previous finish and the EXTRA-FINE PASTE.
- Mix a bag of Chukum EXTRA-FINE PASTE with Chukum water in a bucket and whisk until a smooth consistency is obtained, dissolving any lumps.
- Once the adhesion bridge is dry, the paste can be applied on the intended surface.
- If the surface is not smooth, a first coat can be applied to level and fill pores, giving a smoother appearance.
- When applying the second coat, it should cover any imperfections reflected in the first coat. It can then be burnished without burning the finish.
- Pigments can be added during the mixing process to obtain different colors. It is recommended to apply a varnish or sealer at the end of the application, for added protection.

NOTE: In the case of CANKAB Chukum, it is advisable not to apply more than one bag per 3 bags of the extra fine product because it will weaken the finish.

CHARACTERISTICS	DESCRIPTION
Density of powdered product	1906 kg/m3
Percentage of mixed water	20%
Resistance to the compression	50 kg/cm2
Percentage of water absorption	4%
Initial setting	3 to 4 hrs.
Final setting	6 to 7 hrs.

Caroline Ramos

□ 551-579-9033

caroline@chukum.com.mx

www.chukumusa.com

© chukumusa

sales@chukum.com.mx